



Metal Finishing Systems

Birchwood Laboratories, Inc.
7900 Fuller Road
Eden Prairie, MN 55344 USA
Tel: 952/937-7931
Fax: 952/937-7979

www.birchwoodcasey.com

ALUMA BLACK® A14 Brush-On Blackener

Operating Instructions

PRODUCT DESCRIPTION

ALUMA BLACK® A14 Brush-On Blackener works at room temperature on all forms of aluminum to form an adherent black finish. Applied by brush-on techniques, the solution carries out a chemical reaction with the metal surface and forms a non-dimensional black finish that is bonded to the surface. Recommended for blackening of engravings or touch-up of aluminum components. A clear, protective topcoat is normally used as a sealant over the A14 black finish.

APPLICATION INSTRUCTIONS

In short, the surface must first be thoroughly cleaned of all oil and transparent oxide. The black finish is then applied, rinsed, dried and sealed with a topcoat appropriate to the end use of the article:

1. CLEAN the metal surface, using a solvent that does not leave a residue. Use alcohol, acetone, lacquer thinner or equivalent. (Do not use mineral spirits or kerosene.)
2. REMOVE OXIDE by bead blasting, or use other abrasive cleaning method, such as satinizing with Scotchbrite® abrasive pads or flapwheels.
3. APPLY ALUMA BLACK A14 solution to the surface by brush, swab or spray techniques (using a plastic pump sprayer). For best results, apply a thin film of solution on the surface, then re-apply a few more times during the course of the reaction in order to “replenish” the supply of chemicals working on the surface. A light duty flooding technique works best. For large surfaces, apply the A14 solution with a wide applicator or with a pump sprayer to facilitate wetting a larger area in a few seconds. Continue application until a uniform gray/black finish is achieved.
4. STOP the REACTION by sponging the surface with warm water to remove blackening residues. Large items or parts with complicated shapes should be rinsed a second time with a baking soda solution (mixed 2 tablespoons per gallon of warm water) to neutralize the surface the inhibit further corrosion during drying.
5. FORCE DRY the surface with compressed air or warm air to speed drying.
6. SEAL the surface with a SATIN SHIELD® SS10 water-based lacquer, or use an oil-based lacquer or wax to protect the black finish. Decorative parts can be highlighted with Scotchbrite, to produce an antique finish, then lacquered.

PACKAGING

1 and 5 gallon containers. Store in closed containers.

Before Using This Product – Please Read, Understand and Follow all the Precautions shown on the Product Label and on the Material Safety Data Sheet.

The Material Safety Data Sheet can be found on our website: www.birchwoodcasey.com

Always Apply Appropriate Labels to any Container used to Store or Apply this Product.

NOTE: The information contained herein is provided in good faith and is believed to be correct as of the date hereof. However, Birchwood Laboratories, Inc. makes no representation as to the comprehensiveness or accuracy of the information. It is expected that individuals receiving the information will exercise their independent judgment in determining its appropriateness for a particular purpose. Accordingly, Birchwood Laboratories, Inc. will not be responsible for damages of any kind resulting from the use of or reliance upon such information.

ALUMA BLACK® A14 (Product Numbers 630050, 630051)

©Birchwood Laboratories, Inc.

May 2007